

Technical Data Sheet

SZ53/00**
CLEAR MATT NITROCELLULOSE TOPCOAT
Supersedes previous issue dated 10/31/03

DATE 07/11/12

Versions:	10, 20, 35, 50, 60, 70 gloss
Area of use:	General purpose.
Method of use:	Airmix, airless, manual spray guns
Mixing procedure:	by weight (kg)
Part A:	SZ53**/00 100
Thinner:	DT0436/00 20

Technical characteristics

Solids content (%):	26 ± 2
Specific gravity (kg/l):	0.950 ± 0.030
Viscosity (DIN 4 at 20°C):	34" ± 2"

Substrate preparation

With AC0600/XX waterborne stains or with XM7100/XX or XM8000/XX solvent-based stains, followed by nitrocellulose, polyurethane or polyester basecoat.

General characteristics

Recommended application weight (g/m²):	Min. 100 - Max. 150
Drying time (100 g/m² at 20°C):	Dust free 10' Touch dry 1 hour Through dry 2 hours
Shelf-life (months):	36 After long periods of storage, always check homogeneity and stir well before use to eliminate any possible sediment.

SZ53**/00 exhibits good build and smoothness.

Special instructions

In particularly hot or humid weather it is advisable to add 2-7% of XS0007/00 (anti-blushing thinner) to prevent blooming and improve flow. For light tinting, use XC1900/XX concentrated stains.