

# Technical Data Sheet

## TZL3471/00 MAT CLEAR ACRYLIC TOPCOAT

DATE 03/27/15

Versions:	3 gloss.
Area of use:	Frames, flat parts and turned parts
Method of use:	airmix
Mixing procedure:	By weight (kg)
Part A:	TZL3471/00 100
Part B (hardener):	THL3355/00 10 – 20
	DT1150/00 30 – 50

### Technical characteristics:

Solids content (%):	17 ± 2
Specific gravity (kg/l):	0.910 ± 0.030
Viscosity (DIN 4 at 20°C):	75" ± 10"

### General characteristics

Pot-life:	5 h
Recommended application weight (g/m²):	Min. 80 - Max. 120
Drying time (100 g/m² at 20°C):	Dust free 10' - 15' Touch dry 20' - 30' Stackable 6 - 8 h
Shelf-life (months):	36 After long periods of storage, always check homogeneity and stir well before use to eliminate any possible sediment.

TZL3471/00 exhibits high scratch resistance, good smoothness and wetting properties.

It is particularly suitable for applications that require natural effect with high yellowing resistance.

Thinner recommended during summer is DT0090/00 which gives the right wettability and speed.