

<b>DOCUMENT ESTABLISHED BY</b>	<b>TECHNICAL DATA</b>	<b>DATE</b>
<b>TECHNICAL SECRETARIAT</b>		<b>CREATION : 20/11/2006</b>  <b>UP DATING :</b>
<b>FOR 03-01/1</b>		

## XE4583 NATURAL OIL

**GLOSSICITY**
**METHOD OF APPLICATION**

Spray gun with wiping after 5 minutes

**HARDENING & THINNING**

No thinner

**TECHNICAL**
**CHARACTERISTICS**
**\*Solids by weight** : 55 % +/- 2

**\*Density** : 0,88 +/- 0,01

**\*Viscosity** : 18" Ca4 +/- 2"

**\*Drying Time for 60g/sqm2 at 20° C** : around 24 hours

**REMARK**

Apply directly on wood.

It's possible to heat the product to 50°C to obtain a better penetration in the wood.

A second application can be done after 2 hours.

XE 4583 is usable for food contact (European Resolution AP (96) 5).

**PRECAUTION: INSULATE THE WIPING RAGS  
AFTER USE**
**HSE LABEL**

Xn

Inflammable

**SHELF LIFE**

1 year